



AIRLISS G

GENERAL INFORMATION

Description

Ready mixed
spray-applied plaster
Special airless
formulation

Intended use

- Interior
- Levelling and finishing substrates

Manual application



Use



interior

Application thickness



5 mm

Ready mixed

Mechanical application



Spray and airless machine

Roller application



Advantages

- + One product for both levelling & finishing
- + Easy to sand
- + White
- + Fine finish
- + Manual or mechanical application

USE

DILUTION Ready mixed

PREPARATION Stir before use (dilute up to 3% if necessary)

APPLICATION

Conditions Do not apply at temperatures of below 8°C or above 35°C, or at a relative humidity of above 70% H.R.

Equipment Smoothing trowel, blade, dedicated roller

Machine Airless machine - 5 l/min (tip size up to 5.31).
Neither strainer nor filter needed for application.
Screw-pump machine (nozzle up to 6 mm).

Equipment cleaning With water before completely dry.
Do not throw away into drains, dispose of this material and its container to an approved disposal contractor or taken to municipal collection point.
Do not dispose into the environment.

APPLICATION THICKNESS 5 mm

AVERAGE CONSUMPTION 1 to 3 kg/m²

SUBSTRATES Concrete, cellular concrete, cement, concrete block, brick, plaster, plasterboard, old painted substrates, old sprinkle effect, glass cloth.
Substrates must be hard, cohesive, clean, sound and dry according to the local standards.

OVERCOAT Primer, interior conventional paint, light-weight wall coverings.




Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

AIRLISS G

TECHNICAL DATA



| | |
|--|--|
| COMPONANTS | Polymer base aqueous phase coat mix, mineral fillers, additives. 97 % of raw materials of natural origin (Calcium carbonate, talc, water, clay, sugar) |
| DENSITY | 1.7 ± 0,1 |
| pH | 9,4 ± 0,5 |
| COLOUR | White |
| WAITING TIME BEFORE OVERCOATING | Once completely dry |
| CLASSIFICATION | NF T 36-005 - Family III, class 2 |
| NORM | NF EN 16566 NF ENVIRONNEMENT : Enduits de peinture - NF 446 The certified characteristics are available from AFNOR Certification 11 rue de Pressensé 93571 La Plaine Saint-Denis Cedex - France or on www.ecolabels.fr |
| V.O.C. | < 1 g/l (ready mixed) |
| HEALTH AND SAFETY |  Use in a well-ventilated place. Avoid direct contact with skin and eyes. Do not breathe dust. In case of prolonged contact, it is recommended to wear suitable gloves. During application by projection, wearing glasses and a mask is recommended. Safety data sheet available on www.beissier.eu or www.quickfds.com |
| PACKAGING | 25 kg bag and 25 kg bucket |
| STORAGE | 12 months from date of manufacture, in unopened original packaging, protected from frost, heat (max. + 30°C) sun and moisture. Close well after use. Store in original packaging |

This data sheet supersedes and replaces any prior sheet relating to the same product.

Date of issue : February 2024

The purpose of this data sheet is to inform our customers about our product's properties. The information presented in the sheet is based on the current state of our knowledge. However, this information is no substitute for a description pertaining specifically to the type and condition of the substrate concerned. Since technical progress is continuously being made, it is our customer's responsibility, prior to use, to check with us that updated edition of this sheet has not been issued.

Beissier

Applying excellence

BEISSIER | Becket House - 1 Lambeth Palace Road - LONDON - SE1 7EU

Customer service : ☎ 020 7092 6696 | contact@beissier.eu