



Advantages

- + 4 IN 1**
 - Plasterboard jointing compound
 - Filling up to 8 mm
 - Crack repair
 - Levelling block work
 - Skim coating surfaces
- + Application**
 - Very smooth application
 - Light weight
 - Apply with roller, trowel or blade
- + Easy to sand**
- + Fine finish**
- + White**



ENDUITS DE PEINTURE
NF 446

www.ecolabels.fr



Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).



MULTI-LIGHT FILLER

GENERAL INFORMATION

Description

Ready mixed
light weight
multipurpose filler

Intended use

- Interior
- Taping & jointing plasterboard
- Filling small holes and cracks
- Skim coating

Roller
application



Manual
application



Use



Application
thickness



Working
time



Ready
mixed

USE

DILUTION Ready mixed

APPLICATION

Conditions Do not apply at temperatures of below + 8°C or above + 35°C, or at a relative humidity of above 70% H.R.

Equipment Filling knife, blade, dedicated roller

Equipment cleaning With water before completely dry. Do not throw away into drains, dispose of this material and its container to an approved disposal contractor or taken to municipal collection point. Do not dispose into the environment.

APPLICATION THICKNESS 8 mm

AVERAGE CONSUMPTION 1,3 kg/m²

SUBSTRATES Concrete, cellular concrete, cement, concrete block, brick, plaster, plasterboard, old painted substrates, old sprinkle effect, glass cloth.
Substrates must be hard, cohesive, clean, sound and dry according to the local standards.

OVERCOAT Primer, conventional paint, light-weight wall coverings.



MULTI-LIGHT FILLER

TECHNICAL DATA

COMPONANTS	Polymer base aqueous phase coat mix, mineral fillers, additives 90% of raw materials of natural origin (Calcium carbonate, water, clay, starch)
DENSITY	1,3 ± 0,1
pH	9 ± 1
COLOUR	White
WORKING TIME AT 20°C	Unlimited
WAITING TIME BEFORE OVERCOATING	Once completely dry
CLASSIFICATION	NF T 36-005 - Family III, class 2
NORM	NF EN 16566 - NF EN 13963, type 3A
	NF ENVIRONNEMENT : Enduits de peinture - NF 446 The certified characteristics are available from AFNOR Certification 11 rue de Pressensé 93571 La Plaine Saint-Denis Cedex - France or on www.ecolabels.fr
V.O.C.	< 1 g/l (ready mixed)

HEALTH AND SAFETY



Use in a well-ventilated place. Avoid direct contact with skin and eyes. Do not breathe dust. In case of prolonged contact, it is recommended to wear suitable gloves. Safety data sheet available on www.beissier.eu or www.quickfds.com

PACKAGING

12 kg and 4 kg bucket

STORAGE

12 months from date of manufacture, in unopened original packaging, protected from frost, heat (max. + 30°C) sun and moisture. Close well after use. Store in original packaging

	Jointing materials for gypsum plasterboards EN 13963 : 2014 Type 3A
	PRESTONETT MULTI-LIGHT FILLER
BEISSIER - Quartier de la gare - 77760 LA CHAPELLE LA REINE FRANCE	
Reaction to fire	A2-s1, d0
Flexural Strength	NPD

This data sheet supersedes and replaces any prior sheet relating to the same product.

Date of issue : January 2024

The purpose of this data sheet is to inform our customers about our product's properties. The information presented in the sheet is based on the current state of our knowledge. However, this information is no substitute for a description pertaining specifically to the type and condition of the substrate concerned. Since technical progress is continuously being made, it is our customer's responsibility, prior to use, to check with us that updated edition of this sheet has not been issued.

Beissier

Applying excellence

BEISSIER | Becket House - 1 Lambeth Palace Road - LONDON - SE1 7EU

Customer service : ☎ 020 7092 6696 | contact@beissier.eu